



Zhejiang Narada Power Source Co., Ltd.

East Wing, No.822 Wen'er Xi Road, Hangzhou 310030, P.R.China.

Tel: +86 571 56975980; Fax: +86 571 56975955; Website: en.naradapower.com; Email: intl@naradapower.com

Supported Table and Graph for Narada 48NPFC100 (High Cycle Mode)

List of Content

1. **Table 1** Cycle life at different DOD 100%, 80%, 60%, 40% based on different temperature 25°C, 30°C, 35°C, 40°C, 45°C in 0.2C discharge current.
2. **Table 2** Discharge voltage at DOD 20%, 40%, 60%, 80%, 90%, 95% with different discharge rate: 0.1Crt, 0.2Crt, 0.5Crt, 0.8Crt, 1.0Crt
3. **Table 3** Total energy (Wh) that the battery can discharge in whole life with different DODs
4. **Table 4** Capacity by discharge at 25 °C, 100% DoD deep discharge with discharge lines 0.2C, 0.5C, 0.8C and at 45 °C with discharge @ 0.2C for 48NPFC100.

Zhejiang Narada Power Source Co., Ltd.

East Wing, No.822 Wen'er Xi Road, Hangzhou 310030, P.R.China.

Tel: +86 571 56975980; Fax: +86 571 56975955; Website: en.naradapower.com; Email: intl@naradapower.com

Table 1 Cycle life at different DOD 100%, 80%, 60%, 40%
at different temperature: 25°C, 30°C, 35°C, 40°C, 45°C, discharge at 0.2Crt

Temp (°C)	Depth of Discharge (%)			
	100%	80%	60%	40%
25	4800	6000	8200	12000
30	4300	5400	7200	10500
35	3900	4800	6400	9000
40	3400	4200	5400	7500
45	2100	2600	3500	5200

Table 2.1 Module discharge voltage at DOD 20%, 40%, 60%, 80%, 90%, 95%
with different discharge rate: 0.1Crt, 0.2Crt, 0.5Crt, 0.8Crt, 1Crt

DOD\Discharge rate	0.1C	0.2C	0.5C	0.8C	1C
20%	49.55V	49.19V	48.54V	48.17V	47.76V
40%	49.04V	48.77V	48.27V	47.93V	47.58V
60%	48.87V	48.51V	47.91V	47.57V	47.21V
80%	48.24V	47.91V	47.30V	46.92V	46.47V
90%	47.54V	47.22V	46.64V	46.28V	45.18V
95%	47.03V	46.65V	45.92V	45.60V	43.43V

Table 2.2 Cell discharge voltage at DOD 20%, 40%, 60%, 80%, 90%, 95%
with different discharge rate: 0.1Crt, 0.2Crt, 0.5Crt, 0.8Crt, 1Crt

DOD\Discharge rate	0.1C	0.2C	0.5C	0.8C	1C
20%	3.303V	3.279V	3.236V	3.211V	3.184V
40%	3.269V	3.251V	3.218V	3.195V	3.172V
60%	3.258V	3.234V	3.194V	3.171V	3.147V
80%	3.216V	3.194V	3.153V	3.128V	3.098V
90%	3.169V	3.148V	3.109V	3.085V	3.012V
95%	3.135V	3.110V	3.061V	3.040V	2.895V

Zhejiang Narada Power Source Co., Ltd.

East Wing, No.822 Wen'er Xi Road, Hangzhou 310030, P.R.China.

Tel: +86 571 56975980; Fax: +86 571 56975955; Website: en.naradapower.com; Email: intl@naradapower.com**Table 3** Total energy (Wh) @25°C that the battery can discharge in whole life with different DODs

DOD (%)	Cycle life	Energy KWh/0.2C
100%	4800	11040
80%	6000	13056
60%	8200	12096
40%	12000	12096

Table 4 Capacity by discharge @ 25 °C, 100% DoD deep discharge with discharge lines 0.2C, 0.5C, 0.8C

Model No.	Temperature	Discharge rate	End voltage	Capacity
48NPFC100	25DegC	0.2C	43.2V	≥100Ah
		0.5C		≥98Ah
		0.8C		≥96Ah
	45DegC	0.2C		≥100Ah

Hangzhou, August 2nd, 2024

Zhejiang Narada Power Source Co., Ltd

